



# Standard Specification for Pressure Vessel Plates, Carbon Steel, Low- and Intermediate-Tensile Strength<sup>1</sup>

This standard is issued under the fixed designation A 285/A285M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope\*

1.1 This specification<sup>2</sup> covers carbon steel plates of low- and intermediate-tensile strengths which may be made by killed, semi-killed, capped, or rimmed steel practices at the producer's option. These plates are intended for fusion-welded pressure vessels.

1.2 Plates under this specification are available in three grades having different strength levels as follows:

Grade	Tensile Strength, ksi [MPa]
A	45–65 [310–450]
B	50–70 [345–485]
C	55–75 [380–515]

1.3 The maximum thickness of plates under this specification, for reasons of internal soundness, is limited to a maximum thickness of 2 in. [50 mm] for all grades.

NOTE 1—For killed carbon steels only refer to the following ASTM specifications:<sup>3</sup>

A 299/A 299M Pressure Vessel Plates, Carbon Steel, Manganese-Silicon.

A 515/A 515M Pressure Vessel Plates, Carbon Steel, for Intermediate- and Higher-Temperature Service.

A 516/A 516M Pressure Vessel Plates, Carbon Steel, for Moderate- and Lower-Temperature Service.

1.4 For plates produced from coil and furnished without heat treatment or with stress relieving only, the additional requirements, including additional testing requirements and the reporting of additional test results, of Specification A 20/A 20M apply.

1.5 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must

be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

## 2. Referenced Documents

### 2.1 ASTM Standards:

A 20/A 20M Specification for General Requirements for Steel Plates for Pressure Vessels<sup>3</sup>

## 3. General Requirements and Ordering Information

3.1 Plates supplied to this product specification shall conform to Specification A 20/A 20M, which outlines the testing and retesting methods and procedures, permissible variations in dimensions and mass, quality and repair of defects, marking, loading, etc.

3.2 Specification A 20/A 20M also establishes the rules for ordering information that should be complied with when purchasing plates to this specification.

3.3 In addition to the basic requirements of this specification, certain supplementary requirements are available where additional control, testing, or examination is required to meet end use requirements.

3.4 The purchaser is referred to the listed supplementary requirements in this specification and to the detailed requirements in Specification A 20/A 20M.

3.5 Coils are excluded from qualification to this specification until they are processed into finished plate. Plates produced from coil means plates that have been cut to individual lengths from coil. The processor directly controls, or is responsible for, the operations involved in the processing of coils into finished plates. Such operations include decoiling, leveling, cutting to length, testing, inspection, conditioning, heat treatment (if applicable), packaging, marking, loading for shipment, and certification.

NOTE 2—For plates produced from coil and furnished without heat treatment or with stress relieving only, three test results are reported for each qualifying coil. Additional requirements regarding plate produced from coil are described in Specification A 20/A 20M.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.11 on Steel Plates for Boilers and Pressure Vessels.

Current edition approved Sept. 10, 2003. Published October 2003. Originally approved in 1946. Last previous edition approved in 2001 as A 285/A 285M – 01.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-285/SA-285M in Section II of that Code.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 01.04.

\*A Summary of Changes section appears at the end of this standard.



TABLE 1 Chemical Requirements

Elements	Composition, %		
	Grade A	Grade B	Grade C
Carbon, max <sup>A</sup>	0.17	0.22	0.28
Manganese, max			
Heat analysis	0.90	0.90	0.90
Product analysis	0.98	0.98	0.98
Phosphorus, max <sup>A</sup>	0.035	0.035	0.035
Sulfur, max <sup>A</sup>	0.035	0.035	0.035

<sup>A</sup>Applies to both heat and product analyses.

TABLE 2 Tensile Requirements

	Grade A		Grade B		Grade C	
	ksi	[MPa]	ksi	[MPa]	ksi	[MPa]
Tensile strength	45–65	[310–450]	50–70	[345–485]	55–75	[380–515]
Yield strength, min <sup>A</sup>	24	[165]	27	[185]	30	[205]
Elongation in 8 in. or [200 mm], min, % <sup>B</sup>	27		25		23	
Elongation in 2 in. or [50 mm], min, % <sup>B</sup>	30		28		27	

<sup>A</sup>Determined by either the 0.2 % offset method or the 0.5 % extension-under-load method.

<sup>B</sup>See Specification A 20/A 20M for elongation adjustment.

3.6 If the requirements of this specification are in conflict with the requirements of Specification A 20/A 20M, the requirements of this specification shall prevail.

#### 4. Heat Treatment

4.1 Plates are normally supplied in the as-rolled condition. The plates may be ordered normalized or stress relieved, or both.

#### 5. Chemical Composition

5.1 The steel shall conform to the requirements as to chemical composition as given in Table 1.

#### 6. Mechanical Properties

6.1 *Tension Test*—The plates, as represented by the tension test specimens, shall conform to the requirements given in Table 2.

### SUPPLEMENTARY REQUIREMENTS

Supplementary requirements shall not apply unless specified in the purchase order.

A list of standardized supplementary requirements for use at the option of the purchaser is included in Specification A 20/A 20M. Those that are considered suitable for use with this specification are listed below by title.

S3. Simulated Post-Weld Heat Treatment of Mechanical Test Coupons, and

S4. Additional Tension Test.

### ADDITIONAL SUPPLEMENTARY REQUIREMENTS

Also listed below are additional optional supplementary requirements suitable for this specification:

#### S57. Copper-Bearing

S57.1 The copper content, by heat analysis shall be 0.20–0.35 % and by product analysis 0.18–0.37 %.

#### S58. Restricted Copper

S58.1 The maximum incidental copper content by heat analysis shall not exceed 0.25 %.

**SUMMARY OF CHANGES**

Committee A01 has identified the location of selected changes to this standard since the last issue (A 285/A 285M – 01) that may impact the use of this standard.

(1) 1.4, 3.5, and Note 2 were revised to be consistent with the terminology and requirements of Specification A 20/A 20M.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*