



Standard Specification for Straight-Beam Ultrasonic Examination of Plain and Clad Steel Plates for Special Applications¹

This standard is issued under the fixed designation A 578/A578M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification² covers the procedure and acceptance standards for straight-beam, pulse-echo, ultrasonic examination of rolled carbon and alloy plain and clad steel plates, $\frac{3}{8}$ in. [10 mm] in thickness and over, for special applications. The method will detect internal discontinuities parallel to the rolled surfaces. Three levels of acceptance standards are provided. Supplementary requirements are provided for examination of clad plate and for alternative procedures.

1.2 Individuals performing examinations in accordance with this specification shall be qualified and certified in accordance with the requirements of the latest edition of ASNT SNT-TC-1A or an equivalent accepted standard. An equivalent standard is one which covers the qualification and certification of ultrasonic nondestructive examination candidates and which is acceptable to the purchaser.

1.3 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

A 263 Specification for Corrosion-Resisting Chromium Steel-Clad Plate, Sheet, and Strip³

A 264 Specification for Stainless Chromium-Nickel Steel-

Clad Plate, Sheet, and Strip³

A 265 Specification for Nickel and Nickel-Base Alloy-Clad Steel Plate³

2.2 ANSI Standard:

B 46.1 Surface Texture⁴

2.3 ASNT Standard:

SNT-TC-1A⁵

3. Ordering Information

3.1 The inquiry and order shall indicate the following:

3.1.1 Acceptance level requirements (Sections 7, 8, and 9). Acceptance Level B shall apply unless otherwise agreed to by purchaser and manufacturer.

3.1.2 Any additions to the provisions of this specification as prescribed in 5.2, 13.1, and Section 10.

3.1.3 Supplementary requirements, if any.

4. Apparatus

4.1 The amplitude linearity shall be checked by positioning the transducer over the depth resolution notch in the IIW or similar block so that the signal from the notch is approximately 30 % of the screen height, and the signal from one of the back surfaces is approximately 60 % of the screen height (two times the height of the signal from the notch). A curve is then plotted showing the deviations from the above established 2:1 ratio that occurs as the amplitude of the signal from the notch is raised in increments of one scale division until the back reflection signal reaches full scale, and then is lowered in increments of one scale division until the notch signal reaches one scale division. At each increment the ratio of the two signals is determined. The ratios are plotted on the graph at the position corresponding to the larger signal. Between the limits of 20 and 80 % of the screen height, the ratio shall be within 10 % of 2:1. Instrument settings used during inspection shall not cause variation outside the 10 % limits established above.

4.2 The transducer shall be 1 or $1\frac{1}{8}$ in. [25 or 30 mm] in diameter or 1 in. [25 mm] square.

¹ This specification is under the jurisdiction of ASTM Committee A-1 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.11 on Steel Plates for Boilers and Pressure Vessels.

Current edition approved Sept. 10, 1996. Published November 1996. Originally published as A 578 – 67 T. Last previous edition A 578/A 578M – 92.

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-578/SA-578M in Section II of that Code.

³ Annual Book of ASTM Standards, Vol 01.03.

⁴ Available from American National Standards Institute, 11 W. 42nd St., 13th floor, New York, NY 10036.

⁵ Available from American Society for Nondestructive Testing, 1711 Arlington Plaza, Columbus, OH 43228.

4.3 Other search units may be used for evaluating and pinpointing indications.

5. Procedure

5.1 Perform the inspection in an area free of operations that interfere with proper performance of the test.

5.2 Unless otherwise specified, make the ultrasonic examination on either major surface of the plate.

5.3 The plate surface shall be sufficiently clean and smooth to maintain a first reflection from the opposite side of the plate at least 50 % of full scale during scanning. This may involve suitable means of scale removal at the manufacturer's option. Condition local rough surfaces by grinding. Restore any specified identification which is removed when grinding to achieve proper surface smoothness.

5.4 Perform the test by one of the following methods: direct contact, immersion, or liquid column coupling. Use a suitable couplant such as water, soluble oil, or glycerin. As a result of the test by this method, the surface of plates may be expected to have a residue of oil or rust or both.

5.5 A nominal test frequency of 2¼ MHz is recommended. When testing plates less than ¾ in. [20 mm] thick a frequency of 5 MHz may be necessary. Thickness, grain size or microstructure of the material and nature of the equipment or method may require a higher or lower test frequency. Use the transducers at their rated frequency. A clean, easily interpreted trace pattern should be produced during the examination.

5.6 Scanning:

5.6.1 Scanning shall be along continuous perpendicular grid lines on nominal 9-in. [225-mm] centers, or at the option of the manufacturer, shall be along continuous parallel paths, transverse to the major plate axis, on nominal 4-in. [100-mm] centers, or shall be along continuous parallel paths parallel to the major plate axis, on 3-in. [75-mm] or smaller centers. Measure the lines from the center or one corner of the plate with an additional path within 2 in. [50 mm] of all edges of the plate on the searching surface.

5.6.2 Conduct the general scanning with an instrument adjustment that will produce a first reflection from the opposite side of a sound area of the plate from 50 to 90 % of full scale. Minor sensitivity adjustments may be made to accommodate for surface roughness.

5.6.3 When a discontinuity condition is observed during general scanning adjust the instrument to produce a first reflection from the opposite side of a sound area of the plate of 75 ± 5 % of full scale. Maintain this instrument setting during evaluation of the discontinuity condition.

6. Recording

6.1 Record all discontinuities causing complete loss of back reflection.

6.2 For plates ¾ in. [20 mm] thick and over, record all indications with amplitudes equal to or greater than 50 % of the initial back reflection and accompanied by a 50 % loss of back reflection.

NOTE 1—Indications occurring midway between the initial pulse and the first back reflection may cause a second reflection at the location of the first back reflection. When this condition is observed it shall be investigated additionally by use of multiple back reflections.

6.3 Where grid scanning is performed and recordable conditions as in 6.1 and 6.2 are detected along a given grid line, the entire surface area of the squares adjacent to this indication shall be scanned. Where parallel path scanning is performed and recordable conditions as in 6.1 and 6.2 are detected, the entire surface area of a 9 by 9-in. [225 by 225-mm] square centered on this indication shall be scanned. The true boundaries where these conditions exist shall be established in either method by the following technique: Move the transducer away from the center of the discontinuity until the height of the back reflection and discontinuity indications are equal. Mark the plate at a point equivalent to the center of the transducer. Repeat the operation to establish the boundary.

7. Acceptance Standard—Level A

7.1 Any area where one or more discontinuities produce a continuous total loss of back reflection accompanied by continuous indications on the same plane that cannot be encompassed within a circle whose diameter is 3 in. [75 mm] or ½ of the plate thickness, whichever is greater, is unacceptable.

8. Acceptance Standards—Level B

8.1 Any area where one or more discontinuities produce a continuous total loss of back reflection accompanied by continuous indications on the same plane that cannot be encompassed within a circle whose diameter is 3 in. [75 mm] or ½ of the plate thickness, whichever is greater, is unacceptable.

8.2 In addition, two or more discontinuities smaller than described in 8.1 shall be unacceptable unless separated by a minimum distance equal to the greatest diameter of the larger discontinuity or unless they may be collectively encompassed by the circle described in 8.1.

9. Acceptance Standard—Level C

9.1 Any area where one or more discontinuities produce a continuous total loss of back reflection accompanied by continuous indications on the same plane that cannot be encompassed within a 1-in. [25-mm] diameter circle is unacceptable.

10. Report

10.1 Unless otherwise agreed to by the purchaser and the manufacturer, the manufacturer shall report the following data:

10.1.1 All recordable indications listed in Section 6 on a sketch of the plate with sufficient data to relate the geometry and identity of the sketch to those of the plate.

10.1.2 Test parameters including: Make and model of instrument, test frequency, surface condition, transducer (type and frequency), and couplant.

10.1.3 Date of test.

11. Inspection

11.1 The inspector representing the purchaser shall have access at all times, while work on the contract of the purchaser is being performed, to all parts of the manufacturer's works that concern the ultrasonic testing of the material ordered. The manufacturer shall afford the inspector all reasonable facilities to satisfy him that the material is being furnished in accordance with this specification. All tests and inspections shall be made at the place of manufacture prior to shipment, unless otherwise

specified, and shall be conducted without interfering unnecessarily with the manufacturer's operations.

12. Rehearing

12.1 The manufacturer reserves the right to discuss rejectable ultrasonically tested plate with the purchaser with the object of possible repair of the ultrasonically indicated defect before rejection of the plate.

13. Marking

13.1 Plates accepted according to this specification shall be identified by stenciling (stamping) "UT A 578—A" on one

corner for Level A, "UT A 578—B" for Level B, and "UT A 578—C" for Level C. The supplement number shall be added for each supplementary requirement ordered.

14. Keywords

14.1 nondestructive testing; pressure containing parts; pressure vessel steels; steel plate for pressure vessel applications; steel plates; ultrasonic examinations

SUPPLEMENTARY REQUIREMENTS

These supplementary requirements shall apply only when individually specified by the purchaser. When details of these requirements are not covered herein, they are subject to agreement between the manufacturer and the purchaser.

S1. Scanning

S1.1 Scanning shall be continuous over 100 % of the plate surface.

S2. Acceptance Standard

S2.1 Any recordable condition listed in Section 6 that (1) is continuous, (2) is on the same plane (within 5 % of the plate thickness), and (3) cannot be encompassed by a 3-in. [75-mm] diameter circle, is unacceptable. Two or more recordable conditions (see Section 5), that (1) are on the same plane (within 5 % of plate thickness), (2) individually can be encompassed by a 3-in. [75-mm] diameter circle, (3) are separated from each other by a distance less than the greatest dimension of the smaller indication, and (4) collectively cannot be encompassed by a 3-in. [75-mm] diameter circle, are unacceptable.

S2.2 An acceptance level more restrictive than Section 7 or 8 shall be used by agreement between the manufacturer and purchaser.

S3. Procedure

S3.1 The manufacturer shall provide a written procedure in accordance with this specification.

S4. Certification

S4.1 The manufacturer shall provide a written certification of the ultrasonic test operator's qualifications.

S5. Surface Finish

S5.1 The surface finish of the plate shall be conditioned to a maximum 125 μin . [3 μm] AA (see ANSI B 46.1) prior to test.

S6. Examination of Integrally Bonded Clad Plate, Acceptance Level S 6

S6.1 Examine the plate from the clad surface using procedures and techniques in accordance with this specification.

S6.2 Inspect the backing steel to Level B or, if specifically requested by customer, to Level A or Level C.

S6.3 The cladding shall be interpreted to be unbonded when there is complete loss of back reflection accompanied by an echo indication from the plane of the interface of the clad and backing steel.

S6.4 Unless otherwise specified, indications of unbond determined in accordance with S 6.3 that cannot be encompassed within a 3-in. [75-mm] diameter circle shall be weld repaired subject to the requirements and limitations for the repair of defects in cladding of the appropriate material specification.

S6.5 This supplementary requirement is applicable to Specifications A 263, A 264, and A 265.

S7. Examination of Integrally Bonded Clad Plate, Acceptance Level S 7

S7.1 The plate shall be examined from the clad surface using procedures and techniques according to this specification except 100 % surface search is mandatory.

S7.2 Inspect the backing steel to Level B or, if specifically requested by customer, to Level A or Level C.

S7.3 The cladding shall be interpreted to be unbonded when there is complete loss of back reflection accompanied by an echo indication from the plane of the interface of the clad and backing steel.

S7.4 Unless otherwise specified, indications of unbond determined in accordance with S 7.3 that cannot be encompassed within a 1-in. [25-mm] diameter circle shall be weld repaired subject to the requirements and limitations for the repair of defects in cladding of the appropriate material specification. Additionally, prior approval must be obtained if the weld repaired surface exceeds 1.5 % of the cladding surface.

S7.5 This supplementary requirement is applicable to Specifications A 263, A 264, and A 265.

S8. Ultrasonic Examination Using Flat Bottom Hole Calibration (for Plates 4 in. [100 mm] Thick and Greater)

S8.1 Use the following calibration and recording procedures

in place of 5.6.2, 5.6.3, and Section 6.

S8.2 The transducer shall be in accordance with 4.2.

S8.3 *Reference Reflectors*—The $T/4$, $T/2$, and $3T/4$ deep flat bottom holes shall be used to calibrate the equipment. The flat bottom hole diameter shall be in accordance with Table S8.1. The holes may be drilled in the plate to be examined if they can be located without interfering with the use of the plate, in a prolongation of the plate to be examined, or in a reference block of the same nominal composition, and thermal treatment as the plate to be examined. The surface of the reference block shall be no better to the unaided eye than the plate surface to be examined. The reference block shall be of the same nominal thickness (within 75 to 125 % or 1 in. [25 mm] of the examined plate, whichever is less) and shall have acoustical properties similar to the examined plate. Acoustical similarity is presumed when, without a change in instrument setting, comparison of the back reflection signals between the reference block and the examined plate shows a variation of 25 % or less.

S8.4 Calibration Procedure:

S8.4.1 Couple and position the search unit for maximum amplitudes from the reflectors at $T/4$, $T/2$, and $3T/4$. Set the instrument to produce a 75 ± 5 % of full scale indication from the reflector giving the highest amplitude.

S8.4.2 Without changing the instrument setting, couple and position the search unit over each of the holes and mark on the screen the maximum amplitude from each hole and each minimum remaining back reflection.

S8.4.3 Mark on the screen half the vertical distance from the sweep line to each maximum amplitude hole mark. Connect the maximum amplitude hole marks and extend the line through the thickness for the 100 % DAC (distance amplitude correction curve). Similarly connect and extend the half maximum amplitude marks for the 50 % DAC.

S8.5 Recording:

S8.5.1 Record all areas where the remaining back reflection is smaller than the highest of the minimum remaining back reflections found in S 8.4.2.

S8.5.2 Record all areas where indications exceed 50 % DAC.

S8.5.3 Where recordable conditions listed in S 8.5.1 and S 8.5.2 are detected along a given grid line, continuously scan the entire surface area of the squares adjacent to the condition and record the boundaries or extent of each recordable condition.

S8.6 Scanning shall be in accordance with 5.6.

S8.7 The acceptance levels of Section 7 or 8 shall apply as specified by the purchaser except that the recordable condition shall be as given in S 8.5.

TABLE S8.1 Calibration Hole Diameter as a Function of Plate Thickness (S8)

Plate Thickness, in. [mm]	4–6 [100–150]	>6–9 [>150–225]	>9–12 [>225–300]	>12–20 [>300–500]
Hole Diameter, in. [mm]	5/8 [16]	3/4 [19]	7/8 [22]	1 1/8 [29]

S9. Ultrasonic Examination of Electroslag Remelted (ESR) and Vacuum-Arc Remelted (VAR) Plates, from 1 to 16 in. [25 to 400 mm] in Thickness, Using Flat-Bottom Hole Calibration and Distance-Amplitude Corrections

S9.1 The material to be examined must have a surface finish of 200 μ in. [5 μ m] as maximum for plates up to 8 in. [200 mm] thick, inclusive, and 250 μ in. [6 μ m] as maximum for plates over 8 to 16 in. [200 to 400 mm] thick.

S9.2 Use the following procedures in place of 5.6.1, 5.6.2, 5.6.3, and Section 6.

S9.3 The transducer shall be in accordance with 4.2.

S9.4 *Reference Reflectors*—The $T/4$, $T/2$, and $3T/4$ deep flat bottom holes shall be used to calibrate the equipment. The flat bottom hole diameter shall be in accordance with Table S9.1. The flat bottoms of the holes shall be within 1° of parallel to the examination surface. The holes may be drilled in the plate to be examined if they can be located without interfering with the use of the plate, in a prolongation of the plate to be examined, or in a reference block of the same nominal composition and thermal treatment as the plate to be examined. The surface of the reference block shall be no better to the unaided eye than the plate surface to be examined. The reference block shall be of the same nominal thickness (within 75 to 125 % or 1 in. [25 mm] of the examined plate, whichever is less) and shall have acoustical properties similar to the examined plate. Acoustical similarity is presumed when, without a change in instrument setting, comparison of the back reflection signals between the reference block and the examined plate shows a variation of 25 % or less.

TABLE S9.1 Calibration Hole Diameter as a Function of Plate Thickness (S9)

Plate Thickness, in. [mm]	1–4 [25–100]	>4–8 [>100–200]	>8–12 [>200–300]	>12–16 [>300–400]
Hole Diameter, in. [mm]	1/8 [3]	1/4 [6]	3/8 [10]	1/2 [13]

S9.5 Calibration Procedure:

S9.5.1 Couple and position the search unit for maximum amplitudes from the reflectors at $T/4$, $T/2$, and $3T/4$. Set the instrument to produce a 75 ± 5 % of full-scale indication from the reflector giving the highest amplitude.

S9.5.2 Without changing the instrument setting, couple and position the search unit over each of the holes and mark on the screen the maximum amplitude from each of the holes.

S9.5.3 Mark on the screen half the vertical distances from the sweep line to each maximum amplitude hole mark. Connect the maximum amplitude hole marks and extend the line through the thickness for the 100 % DAC (distance amplitude correction curve). Similarly connect and extend the half maximum amplitude marks for the 50 % DAC.

S9.6 *Scanning*—Scanning shall cover 100 % of one major plate surface, with the search unit being indexed between each pass such that there is at least 15 % overlap of adjoining passes in order to assure adequate coverage for locating discontinuities.

S9.7 *Recording*—Record all areas where the back reflection

 **A 578/A578M**

drops below the 50 % DAC. If the drop in back reflection is not accompanied by other indications on the screen, recondition the surface in the area and reexamine ultrasonically. If the back reflection is still below 50 % DAC, the loss may be due to the metallurgical structure of the material being examined. The material shall be held for metallurgical review by the purchaser and manufacturer.

S9.8 *Acceptance Standards*—Any indication that exceeds the 100 % DAC shall be considered unacceptable. The manufacturer may reserve the right to discuss rejectable ultrasonically examined material with the purchaser, the object being the possible repair of the ultrasonically indicated defect before rejection of the plate.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).